

Colorbond[®] Ultra[™]

COLOUR FOR THE EXTREME



1. High durability polyester coating
2. High corrosion resistant primer coating
3. Pre-treatment
4. ZINCALUME[®] AZ 200
5. Steel substrate base
6. ZINCALUME[®] AZ 200
7. Pre-treatment
8. High corrosion resistant primer coating
9. Reverse coating or high durability polyester coating

ISO CATEGORIES

ISO Category E – VERY SEVERE

Characterised by:

- Heavy salt deposits.
- The almost constant smell of salt spray in the air.
- Close to breaking surf (typically 50-200 metres) as found on exposed coasts.

This environment may be extended inland by prevailing winds and local conditions.

ISO Category D – SEVERE

Characterised by:

- Light salt deposits.
- A frequent smell of salt in the air.
- Typically 200-500 metres from breaking surf as found on exposed coasts.
- In the vicinity of large expanses of calm salt water.

This environment may be extended inland by prevailing winds and local conditions.

ISO Category C – MODERATE

COLORBOND[®] ULTRA[™] RECOMMENDED ROOFING AND CLADDING WARRANTY GUIDE

No warranty 0-50m from breaking surf.

10 years: covering the paint surface against flaking and peeling.

12 years: against perforation as a result of corrosion.

15 years: covering the paint surface against flaking and peeling.

15 years: against perforation as a result of corrosion.

15 years: covering the paint surface against flaking and peeling.

20 years: against perforation as a result of corrosion.

VERY SEVERE

SEVERE

MODERATE

Colorbond[®] XRW[™]

PROVEN COLOURS OF THE PACIFIC



1. High durability polyester coating
2. Standard primer coating
3. Pre-treatment
4. ZINCALUME[®] AZ 150
5. Steel substrate base
6. ZINCALUME[®] AZ 150
7. Pre-treatment
8. Standard primer coating
9. Reverse coating

ISO CATEGORIES

ISO Category D – SEVERE

Characterised by:

- Light salt deposits.
- A frequent smell of salt in the air.
- Typically 200-500 metres from breaking surf as found on exposed coasts.
- In the vicinity of large expanses of calm salt water.

This environment may be extended inland by prevailing winds and local conditions.

ISO Category C – MODERATE

Characterised by:

- No obvious marine or industrial influences.
- Little or no salt deposits. The occasional smell of salt in the air.
- Typically 500-1000 metres from breaking surf or more than 500 metres from industrial emissions or in the immediate vicinity of calm salt water.

COLORBOND[®] XRW[™] RECOMMENDED ROOFING AND CLADDING WARRANTY GUIDE

10 years: covering the paint surface against flaking and peeling.

10 years: against perforation as a result of corrosion.

10 years: covering the paint surface against flaking and peeling.

10 years: against perforation as a result of corrosion.

SEVERE

MODERATE